

**DESCRIPTION**

Ceraboard™ is a refractory fibre board supplied in panels of standard thicknesses made from a slurry of refractory fibres and binders which have a low organic content.

The combination of different refractory fibres, inorganic and organic binders in different proportions allows types of boards to be made suitable for different use temperatures.

In some types of heating equipment the emission of fumes, which can occur when binders burn out of the board, can be easily eliminated.

TYPE

Rigid panel based on refractory fibres.

CLASSIFICATION TEMPERATURE

Ceraboard 100:	1260°C
Ceraboard 115:	1400°C

The maximum continuous use temperature depends on the application. In case of doubt, refer to your local Thermal Ceramics distributor for advice.

GRADES AVAILABLE**Ceraboard 100**

This product is recommended for all applications up to 1260°C and where direct flame or hot gas exposure is possible.

Ceraboard 115

This product has a good uniformity of thickness, and possesses good flexural and compressive strengths, before and after heating. It could be used for applications up to 1400°C.

It is ideal as hot face lining, resisting direct flame and hot gas abrasion.

FEATURES

- High temperature stability
- Low thermal conductivity
- Low heat storage
- Rigidity and high cohesive strength allow machining and cutting
- Resistant to thermal shock
- Good erosion resistance
- Can be used in direct contact with flame
- Easy application

APPLICATIONS

These versatile boards can be used where a rigid, self supporting and insulating product is required which also has good resistance to physical damage.

- Ceramic industry (kiln linings & kiln car insulation)
- Glass industry
- Ducts insulation
- General thermal barriers
- High temperature insulation

THICKNESS TOLERANCES

- Less than 10mm: +/- 0.5mm
(except for Ceraboard 100: +/- 1mm)
- From 10mm to 20mm: +/- 1mm
- From 25mm to 50mm: +/- 2mm
- More than 50mm: +/- 4mm

MAIN PROPERTIES

Classification temperature		100	115
	°C	1260	1400

Properties Measured at Ambient Conditions (23°C/50 % RH)

• Colour		white/tan	white/tan
• Density	kg/m ³	310**	310
• Modulus of rupture	MPa	1.0**	0.9
• Compressive stress at 10% relative deformation	MPa	0.35	0.3

High Temperature Performance*

• Loss on ignition after 2 hours heating at 800°C	%	5.5	3.5
• Permanent linear shrinkage (ASTM C-356) after 24 hours isothermal heating at classification temperature:	%	3.0	3.7
• Thermal conductivity (ASTM C-201) at mean temperature of:			

300°C	W/m.K	0.07	0.07
400°C	W/m.K	0.08	0.08
600°C	W/m.K	0.11	0.11
800°C	W/m.K	0.15	0.15
1000°C	W/m.K	0.20	0.20

* Values for thickness 50mm. ** Values 330 and 1.5 for thicknesses below 20mm.

Availability and Packaging

Standard dimensions mm	Ceraboard 100		Ceraboard 115	
	Board per carton	Board per pallet	Board per carton	Board per pallet
1200 x 1000 x 6	20	160		
1200 x 1000 x 7.5	16	120		
1200 x 1000 x 10	12	90		
1200 x 1000 x 13	10	72		
1200 x 1000 x 15	8	60		
1200 x 1000 x 20	6	48		
1200 x 1000 x 25	5	36	5	36
1200 x 1000 x 40	3	24	3	24
1200 x 1000 x 50	2	18	2	18

Ceraboard is packed in cartons or on pallets which are shrink wrapped with recyclable plastic.

Your local contact:

Distributed by:

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information.

Thermal Ceramics Marketing Offices

Thermal Ceramics Americas
 2102 Old Savannah Road
 Augusta, Georgia 30903
 Tel: +1 706 796 4200
 Fax: +1 706 796 4398
 E-mail: tceramics@thermalceramics.com

Thermal Ceramics Asia Pacific
 28 Jalan Kilang Barat
 Kewalram House, Singapore 159362
 Tel: +65 6273 1351
 Fax: +65 6273 0165
 E-mail: thermalceramics@tcasia.com.sg

Thermal Ceramics Europe
 Tebay Road, Bromborough
 Wirral CH62 3PH UK
 Tel: +44 (0) 151 334 4030
 Fax: +44 (0) 151 334 1684
 E-mail: marketing@thermalceramics.co.uk

Website: www.thermalceramics.com