



Thermal Ceramics was first to introduce insulating firebrick (IFB) to the industry in the 1930's. The IFB are manufactured with a unique slurry casting process which creates a network of microporosity which produces low thermal conductivity and good thermal shock characteristics. This process produces brick that are some of the most efficient insulators available in the market. The anorthite mineralogy ($\text{CaO} \cdot \text{Al}_2\text{O}_3 \cdot 2 \text{SiO}_2$) of these low temperature IFB gives them excellent strength at operating temperatures and resistance to corrosive alkali environments.

Features

- Extremely low "K" factors
- Low densities
- Low heat storage
- Excellent strength at room and high temperatures
- Excellent resistance to alkali attack
- Excellent service in applications involving special atmospheres

Applications

- Backup insulation for carbon baking furnaces
- Backup insulation in aluminum electrolytic cells
- Electrical kilns for industrial and hobby use
- Backup insulation for blast furnace stove linings
- Linings for carbonizing furnaces
- Forge furnace linings
- Heat transfer linings

Physical Characteristics

Standard sizes*	9" x 4½" x 2½" and 9" x 4½" x 3" (22.5 cm x 11.25 cm x 6.25 cm and 22.5 cm x 11.25 cm x 7.5 cm)
IFB 23 Tile	9" x 9" x 3" to 24½" x 9" X 3" (22.5 cm x 22.5 cm x 7.5 cm to 61.25 cm x 22.5 cm x 7.5 cm)

* Special sizes available upon request.

Manufacturing Process

K-20, TC-23, TC-23 HS, K-23, K-25 IFB	casting
IFB 23 Tile	slinger

Low Temperature Insulating Firebrick

Product Information

Physical Properties	K-20	TC-23	TC-23 HS	K-23	IFB 23 Tile	K-25
Recommended Hot Face temperature, °F (°C)	2000 (1093)	2300 (1260)	2300 (1260)	2300 (1260)	2300 (1260)	2500 (1371)
Melting temperature, °F (°C)	2750 (1510)	2750 (1510)	2750 (1510)	2750 (1510)	2750 (1510)	2800 (1538)
Density, avg (ASTM C 134)						
lb/9" straight, (kg) (kg)	1.86 (0.84)	2.17-2.52 (0.99-1.15)	2.3 (1.1)	1.86 (0.84)	2.2 (1)	2.3 (1.05)
pcf (kg/m ³)	31 (497)	38-44 (609-705)	40 (641)	31 (497)	37 (593)	40 (641)
Modulus of rupture, (ASTM C 133)						
psi (Mpa)	110 (0.76)	110-160 (0.75-1.03)	140 (1.0)	120 (0.83)	105 (0.72)	140 (0.96)
Cold crushing strength, (ASTM C 133)						
psi (Mpa)	125 (0.86)	140-220 (0.97-1.52)	200 (1.4)	135 (0.93)	125 (0.86)	220 (1.52)
Permanent linear change, % (per ASTM C 120)						
@ 1950°F (1066°C)	0	-	-	-	-	-
@ 2250°F (1232°C)	0	-0.1 to -0.4	0.0	0	0	-
@ 2450°F (1343°C)	-	-	-	-	-	-0.1
Deformation under hot load, % @ 10 psi (ASTM C 16)						
1½ hr @ 2000°F (1093°C)	0	-0.1 to -0.3	0	0	0	-
1½ hr @ 2200°F (1204°C)	-	-	-	-	-	-0.1
Chemical Analysis, nominal, %						
Alumina, Al ₂ O ₃	38	39-43	38.8	38	38.8	45
Silica, SiO ₂	43.6	43-45	47.8	43.6	47.8	38
Ferric oxide, Fe ₂ O ₃	0.4	0.4-0.6	0.4	0.4	0.4	0.2
Titanium oxide, TiO ₂	1.5	1.5-1.9	1.6	1.5	1.6	1.6
Calcium oxide, CaO	16	10-12	10.9	16	10.9	14.5
Magnesium oxide, MgO	0.1	0.1-0.2	0.2	0.1	0.2	0.2
Alkalies, as, Na ₂ O and K ₂ O	0.4	0.4-0.7	0.3	0.4	0.3	0.5
Thermal Conductivity, BTU•in./hr•ft²•°F (w/m•k), ASTM C 201						
Mean temperature						
@ 500°F (260°C)	0.95 (0.13)	1.1-1.2 (0.16-0.17)	1.2 (0.17)	0.95 (0.13)	1.0 (0.14)	1.12 (0.16)
@ 1000°F (538°C)	1.18 (0.17)	1.3-1.4 (0.19-0.20)	1.5 (0.22)	1.18 (0.17)	1.3 (0.18)	1.28 (0.18)
@ 1500°F (815°C)	1.45 (0.21)	1.6-1.7 (0.23-0.25)	1.7 (0.25)	1.45 (0.21)	1.6 (0.23)	1.46 (0.21)
@ 2000°F (1093°C)	1.74 (0.25)	1.75-1.9 (0.25-0.27)	2.0 (0.29)	1.74 (0.25)	1.8 (0.25)	1.65 (0.24)

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information.

Thermal Ceramics is a trademark of The Morgan Crucible Company plc. K is a trademark of Thermal Ceramics.

Marketing Communications Offices

Thermal Ceramics Americas

T: (706) 796 4200

F: (706) 796 4398

Thermal Ceramics Asia Pacific

T: +65 6733 6068

F: +65 6733 3498

Thermal Ceramics Europe

T: +44 (0) 151 334 4030

F: +44 (0) 151 334 1684

North America - Sales Offices

Canada

T: +1 (905) 335 3414

F: +1 (905) 335 5145

Mexico

T: +52 (555) 576 6622

F: +52 (555) 576 3060

United States of America

Eastern Region

T: +1 (800) 338 9284

F: +1 (866) 785 2764

Western Region

T: +1 (866) 785 2738

F: +1 (866) 785 2760

South America - Sales Offices

Argentina

T: +54 (11) 4373 4439

F: +54 (11) 4372 3331

Brazil

T: +55 (21) 2418 1366

F: +55 (21) 2418 1205

Chile

T: +56 (2) 854 1064

F: +56 (2) 854 1952

Colombia

T: +57 (2) 2282935/2282803/2282799

F: +57 (2) 2282935/2282803/23722085

Guatemala

T: +50 (2) 4733 295/6

F: +50 (2) 4730 601

Venezuela

T: +58 (241) 878 3164

F: +58 (241) 878 6712